

KERAFINE 52/54

Description: Paraffin wax Kérafine 52/54

Properties:

	Test Standard	Result	Specifications
Melting point	ASTM D87	52.90	°C
Oil content	ASTM D721	0.43	Wt%
Color (saybolt)	ASTM D156	+28.37	
Light stability		-	
Needle penetration (25°C)	ASTM D1321	+16.5	1/10mm
Needle penetration (37.8°C)	ASTM D1321	-48	1/10mm
Kinematic viscosity (100°C)		-3.514	mm ² /s
Kinematic viscosity (98.8°C)		-	mm ² /s
Odor	ASTM D1833	0	
Mechanical impurity and water	Observing	Negative	
Acid and alkali with water solubility	SH/T0407	Negative	
Flash point		-	
Peroxide number		-	

Packaging:

This product is delivered in slabs (5 slabs per carton), in cartons of 25 kg.

15 November 2022

Active

Distribution

Company

Phone: + 33 (0) 4 75 54 35 05

E-mail : contact@adc-solution.com

SIREN: 432 961 134 SIRET: 432 961 134 00025

123 Rue Marie Curie – CHATEAUNEUF-DU-RHONE

SAS Active Distribution Company au Capital de 163 200 Euros – RCS 432 961 134 VALENCE – T.V.A. FR 64 432 961 134