

## **KERAFINE 95**

**Description:** Paraffin wax KERAFINE 95

**Properties:**

	<b>Method</b>	<b>Result</b>	<b>Specifications</b>
<b>Congealing point</b>	ASTM D 938	73 – 77	°C
<b>Brookfield viscosity (100°C)</b>	ASTM D 3236	7 – 12	cPs
<b>Penetration (25°C)</b>	ASTM D 1321	5 – 8	1/10mm
<b>Colour ASTM</b>	ASTM D 1500	<0.5	

**Packaging:**

This product is delivered in beads, in bags of **25 kg**.

21 November 2022

**Active**

**Distribution**

**Company**

Phone : + 33 (0) 4 75 54 35 05

E-mail : [contact@adc-solution.com](mailto:contact@adc-solution.com)

SIREN : 432 961 134 SIRET : 432 961 134 00025  
123 Rue Marie Curie – CHATEAUNEUF-DU-RHONE

SAS Active Distribution Company au Capital de 163 200 Euros – RCS 432 961 134 VALENCE – T.V.A. FR 64 432 961 134